



## DENSE CASTABLE

<b>DATA SHEET</b>	<b>April-19</b>
-------------------	-----------------

SR NO	CLASSIFICATION	RESULTS
1	Al <sub>2</sub> O <sub>3</sub>	60% Min
2	Fe <sub>2</sub> O <sub>3</sub>	2.5% Max
3	Max Grain Size	5 MM
4	C.C.S Kg/cm <sup>2</sup>	350
	Min 100°C	
5	Linear Change %	± 1.5
6	Max	1550°C / 3 hours.
7	Density	2.33 Min
8	Refractoriness	1683°C
9	Orton (Min)	37
10	Recommended service Temp. (Max)	1650°C