



Refractory Mortar for 1600 °C

DATA SHEET

April-19

SR NO	CLASSIFICATION	RESULTS
1	Fe ₂ O ₃	2%
2	Al ₂ O ₃	62%
3	SiO ₂	35%
4	Others	1%